

PAVING ASPHALT-BITUMEN 50-70 PEN

Penetration @ 25 °C	dmm	EN 1426	50	70
Softening Point "R.& B."	°C	EN 1427	46	54
Breaking Point "FRAASS"	°C	EN 12593	-	-8
Ductility @ 25 °C	cm	CNR-B.U. n° 44	100	-
Solubility in Organic Solvent	% m/m	EN 12592	99	-
Flash Point	°C	EN 22592 (1)	230	-
Wax content	% m/m	EN 12606-1	-	2,2
Resistance to hardening @ 163 °C	% m/m	EN 12607-1	-	0,5
Retained Penetration	%	EN 1426	50	-
Softening point after hardening	°C	EN 1427	48	-
Increase in Softening Point, maximum	°C	EN 1427	-	11